

Synthesis and Physicochemical Transformations of Size-Sorted Graphene Oxide during Simulated Digestion and Its Toxicological Assessment against an In Vitro Model of the Human Intestinal Epithelium

Dimitrios Bitounis, Dorsa Parviz, Xiaoqiong Cao, Carlo A. Amadei, Chad D. Vecitis, Elsie M. Sunderland, Brian D. Thrall, Mingliang Fang, Michael S. Strano,* and Philip Demokritou*

In the last decade, along with the increasing use of graphene oxide (GO) in various applications, there is also considerable interest in understanding its effects on human health. Only a few experimental approaches can simulate common routes of exposure, such as ingestion, due to the inherent complexity of the digestive tract. This study presents the synthesis of size-sorted GO of sub-micrometer- or micrometer-sized lateral dimensions, its physicochemical transformations across mouth, gastric, and small intestinal simulated digestions, and its toxicological assessment against a physiologically relevant, in vitro cellular model of the human intestinal epithelium. Results from real-time characterization of the simulated digesta of the gastrointestinal tract using multi-angle laser diffraction and field-emission scanning electron microscopy show that GO agglomerates in the gastric and small intestinal phase. Extensive morphological changes, such as folding, are also observed on GO following simulated digestion. Furthermore, X-ray photoelectron spectroscopy reveals that GO presents covalently bound N-containing groups on its surface. It is shown that the GO employed in this study undergoes reduction. Toxicological assessment of the GO small intestinal digesta over 24 h does not point to acute cytotoxicity, and examination of the intestinal epithelium under electron microscopy does not reveal histological alterations. Both sub-micrometer- and micrometer-sized GO variants elicit a 20% statistically significant increase in reactive oxygen species generation compared to the untreated control after a 6 h exposure.

1. Introduction

2D engineered nanomaterials (ENMs) are characterized by enormous surface area, anisotropic geometry, and electron confinement in a planar surface that render them good candidates for numerous applications in the electronics, energy, construction, and biomedical industry, among others.^[1–4] Graphene, a single atom-thick allotrope of carbon with its atoms arranged in a hexagonal lattice, is probably the most well-studied 2D ENM. Its discovery in 2004^[5] kick started a wave of interest in 2D nanostructures and nowadays the production of graphene-related materials has already reached several thousand metric tons per year.^[6] Its oxidized counterpart, graphene oxide (GO), has also garnered interest due to its scalable production at declining cost^[7,8] and physical and chemical properties which can be tailored to fit the needs of various applications.^[9] Specifically, its high surface area, versatile chemistry, self-assembling properties, and biodegradability have led to its potential incorporation

Dr. D. Bitounis, Dr. X. Cao, Prof. P. Demokritou
Center for Nanotechnology and Nanotoxicology
Department of Environmental Health
T.H. Chan School of Public Health
Harvard University
655 Huntington Ave, Boston, MA 02115, USA
E-mail: pdemokri@hsph.harvard.edu

Dr. D. Parviz, Prof. M. S. Strano
Department of Chemical Engineering
Massachusetts Institute of Technology
77 Massachusetts Avenue 66-570b, Cambridge, MA 02139, USA
E-mail: strano@mit.edu

Dr. C. A. Amadei, Prof. C. D. Vecitis, Prof. E. M. Sunderland
John A. Paulson School of Engineering and Applied Sciences
Harvard University
29 Oxford St, Cambridge, MA 02138, USA

Prof. B. D. Thrall
Biological Sciences Division
Pacific Northwest National Laboratory
Richland, WA 99354, USA

Prof. M. Fang
School of Civil and Environmental Engineering
Nanyang Technological University
Singapore 639798, Singapore

 The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/smll.201907640>.

DOI: 10.1002/smll.201907640

to existing applications and have also spurred the development of new technologies,^[10,11] with GO currently being explored in the food,^[12] agriculture,^[13] biomedical,^[14] and water purification and remediation industries.^[15] This intense interest in GO is reflected on increasing production forecasts for graphene related materials and is translated to GO-enabled products and services, especially in composite materials. Such development inevitably exposes end-consumers and workforce to GO and its life-cycle by-products, and the scientific community has already undertaken its toxicological profiling.

Myriad studies have already investigated the biological effects of GO on cells, tissues, and animals assuming inhalation or intravenous administration as the most plausible human exposure routes.^[16–18] At the same time, its application in food packaging,^[12] water filtration,^[19] nanomedicine,^[20] and the general potential of carbon-based ENMs in agriculture^[21] suggest that ingestion is another possible route for human exposure to GO. Interestingly, there have only been a handful of studies to explore the toxicodynamics of ingested GO on human intestinal epithelial cells^[22–26] and even fewer *in vivo* studies of its system-wide effects upon oral administration.^[27–29] Even more so, the biotransformations of GO across the gastrointestinal tract (GIT) have remained practically unstudied with only one such published work.^[26] As it stands, the limited literature, discrepancies in utilized GO (size and oxidation state), and *in vitro* methodologies confound the assessment of its physicochemical transformations and biological fate in the GIT.

Engineered nanomaterials are increasingly used in the food industry to enhance product durability and are even used as additives to improve sensory effects and boost nutritional value of food products. The determination of their impact on human health upon ingestion has been attracting the interest of the nanosafety community.^[30] Still, there are knowledge gaps regarding the toxicokinetics of ingested ENMs following absorption from the GIT, their acute and chronic effects on the gastrointestinal barrier, and their toxicodynamics, including biotransformations as they undergo digestion. Food matrix may further modulate the response of biological systems to ingested ENMs^[31,32] and complicate the identification of physical and chemical alterations which might govern their toxicological impact. These alterations include biodissolution,^[33] biomolecular corona formation,^[34] and morphological changes, like agglomeration.^[35] In the case of anisotropic, carbonaceous, soft materials like GO, the technical challenges are ever so harder to overcome and could partially explain the scarcity in available literature.

In order to address the aforementioned knowledge gaps, two distinctly sized populations of GO were synthesized in this study. The synthesized sub-micrometer and a micrometer-sized GO variants were incorporated in a fasting food model (FFM) and submitted to a three-stage (oral, gastric, small intestinal), simulated gastrointestinal digestion according to a methodology previously developed by our group.^[36] The physical and chemical transformations of GO were analyzed by employing multiple techniques. Particularly, real-time, ensemble size measurements of GO were performed using multi-angle laser diffraction to follow its agglomeration along the GIT. Furthermore, a custom-developed sample preparation protocol allowed us to observe microscale alterations on GO's morphology by

means of field-emission scanning electron microscopy. Moreover, it was possible to probe the chemical modifications on the surface of GO after its simulated digestion by means of X-ray photoelectron spectroscopy. Finally, we performed the toxicological assessment of GO digests using a physiologically relevant, tri-culture *in vitro* model of the human small intestinal epithelium consisting of differentiated small intestinal enterocytes (Caco-2 cells), mucus-secreting goblet cell-like cells (HT29), and specialized microfold cells, naturally associated with the lymphatic system.^[36] **Figure 1** summarizes the study design.

2. Results and Discussion

2.1. Synthesis, Size-Sorting, and Physicochemical and Biological Properties of Pristine GO

The preparation of colloidally stable and sterile GO of distinct lateral size is a multistep process of synthesis, purification, and exfoliation. Endotoxin-free synthesis of GO was performed according to an improved Hummer's method previously presented by the authors.^[37] During synthesis, the size of GO flakes and their degree of oxidation depends on multiple factors, like the precursor graphite, ratio of intercalant acids and oxidizing agents, reaction temperature, and duration,^[38] as shown in **Figure 2a**. The purification step allowed removing residual ions and acids as well as large and less oxidized debris. Then, the exfoliation step performed by ultrasonication in water, controlled the size distribution of the flakes depending on the total energy delivered, duration, and GO concentration. At the end of this process, the size distribution of GO is still wide and size heterogeneity confounds its morphology-dependent investigation in biological systems. In this study, post-processing was employed to independently control size to other parameters, like surface chemistry, and thus obtain two GO samples of relatively monodisperse and distinct lateral size. To this date, centrifugation techniques which rely on different sedimentation rate of GO flakes of variable lateral size and thickness are the most successful and scalable size separation methods. Using iterative centrifugation, it is feasible to separate GO flakes of higher mass (of either larger lateral size or thickness) by collecting the precipitate of each iteration and centrifuging the supernatant at an increased *g*-force in next iteration, as shown in **Figure 2b**.

The mean lateral sizes of the pristine sub-micrometer-sized GO (smGO) and micrometer-sized GO (mGO) as measured by field emission electron microscopy (FESEM) were 0.24 and 1.13 μm , respectively, and their size cumulative frequency distributions were found to be significantly different by the Kolmogorov–Smirnov test ($p < 0.0001$). Atomic force microscopy was employed to measure the thickness of the flakes which at 0.8–1.2 nm suggested that GO was mostly organized in single layers. As measured by X-ray photoelectron spectroscopy (XPS), the C/O ratios of smGO and mGO were also similar at 1.37, and 1.41, respectively. Raman spectra of both sizes presented a *D* peak at 1360 cm^{-1} and a *G* peak at 1590 cm^{-1} . Moreover, the I_D/I_G ratios of smGO and mGO, indicative of the functionalized sp^3 -hybridized carbon atoms to sp^2 -hybridized carbon atoms ratio, were ≈ 0.83 and ≈ 0.84 , respectively, suggesting




Figure 1. Stepwise overview of the study. This study presents the preparation of GO-enabled fasting food models, their simulated digestion, physico-chemical characterization, and *in vitro* toxicological assessment against a triculture model of the human small intestinal epithelium.

similar defect density and surface chemistry.^[39] Complete characterization data, including atomic force microscopy thickness and lateral size distributions, FESEM size distributions, XPS survey spectra, Raman spectra, trace metal purity, endotoxin, and microbiological load assessment for smGO and mGO are presented in Tables S1 and S2 in the Supporting Information, respectively.

2.2. Preparation and Colloidal Stability of GO-Enabled Fasting Food Models

smGO- and mGO-enabled fasting food models at 50 and 250 $\mu\text{g mL}^{-1}$ were prepared by respectively dispersing pristine smGO and mGO suspensions in HyClone cell culture grade water following the dispersion protocol presented in the

experimental section. The fasting food model employed here uses water as the simplest possible matrix for the ingestion of GO in absence of nutrients, like fat, carbohydrates, or proteins. Moreover, in the absence of data on human exposure to GO, the chosen concentrations were based on the potential ingestion of GO upon the rupture of a GO-based membrane for water filtration. GO membranes generally operate in the nanofiltration regime with a filtration rate of 1–10 $\text{L m}^{-2} \text{h}^{-1}$ for each applied bar.^[40] Membrane thickness and surface area are typically in the range of $\approx 0.5\text{--}1.0 \mu\text{m}$ and $\approx 10 \text{cm}^2$,^[41] respectively. Given a GO density of $\approx 2 \text{g cm}^{-3}$,^[42] this amounts to a total mass of 1–10 mg.

After preparation, the colloidal properties of GO-enabled fasting food models were measured by dynamic light scattering (DLS) and electrophoretic light scattering, summarized in Table S3 in the Supporting Information. In brief, both smGO and mGO at 50 and 250 $\mu\text{g mL}^{-1}$ presented negative




Figure 2. a) Overview of the preparation of monodisperse GO suspensions including synthesis via oxidation, purification, exfoliation, and size-sorting. b) Schematic of the iterative centrifugation applied for preparation of monodisperse GO suspensions.

z-potential values ranging from -47 to -52 mV. The strongly negative z-potential of GO has been attributed to ionizable carboxylic groups and other ionizable groups with variable pK_a ,^[43] but its excellent dispersibility in aqueous media is mostly due to tertiary alcohol and epoxy groups on its planar surface.^[43,44] Moreover, the polydispersity indices (pdi) of smGO and mGO were below ≈ 0.4 which can be considered relatively low for ENMs produced with top-down approaches. **Figure 3** presents the colloidal stability of as-prepared GO-enabled fasting food models. GO-enabled fasting food models presented stable diffusion coefficients, pdi, and light scattering intensities at both angles over at least 10 min, which is the preparation time for the simulated digestions. In more detail, the regression coefficients (slopes) of agglomeration indices (ai) and mean diffusion coefficients equaled to zero, indicating that particles did not agglomerate. The only exception as shown in Figure 3d was the pdi slope for mGO at $250 \mu\text{g mL}^{-1}$ at 0.1 which suggested slight agglomeration of GO flakes to bodies of variable size. These results overall agree with what is known for the colloidal stability of GO in perineutral water at low ionic strength.^[45] In such environments, sufficiently oxidized graphene flakes experience strong electrostatic repulsion due to negative charges from $-\text{COO}^-$ and other electronegative oxygen-containing functionalities and van der Waals forces and $\pi-\pi$ interactions cannot induce agglomeration.^[46]

2.3. Agglomeration of GO Flakes upon Simulated Gastrointestinal Digestion

Figure 4 shows how smGO and mGO behave across the GIT. In more detail, **Figure 4a** shows that both GO samples present minimal agglomeration in the oral phase. In the gastric phase, as shown in **Figure 4b**, smGO and mGO organize in structures

larger than those present in the blank, due to the acidic pH 2 at which protonation of GO flakes cancels their electrostatic stabilization,^[45] further promoted by the Debye screening of the flakes' surface charge in the presence of salts. In the small intestinal phase, as shown in **Figure 4c**, smGO and mGO agglomerate even further, probably due to the presence of bile salts and additional digestive enzymes. These are expected to adsorb on the surface of GO and further accentuate its agglomeration by bridging and stabilizing clusters of multiple flakes.^[47] Overall, the results of this study are in agreement to what has been previously reported on the agglomeration of GO in the GIT by Guarneri et al.^[26] who suggested that GO agglomerates during simulated digestion based on changes in the D band of digested GO.

It has to be noted that the size distributions obtained by multi-angle laser diffraction (MALD) can be trustworthy when the illuminated particles are spherical, rigid, nontransparent, and share the same refractive index. The anisotropic geometry of GO flakes and the presence of particles with variable refractive indices (e.g., biomolecules) in GO digesta do not conform to the ideal conditions required for MALD. Nevertheless, this technique can still be utilized to qualitatively assess the agglomeration of particulates in complex dispersions (i.e., by setting the same refractive index for all samples, it is possible to compare shifts in size distributions and thus evaluate the agglomeration of GO in real time with minimal sample preparation).

Shifts in size distribution of smGO and mGO were further compared to blank FFM (digesta without the presence of GO), based on the $D_{v,10}$, $D_{v,50}$, and $D_{v,90}$ values which represent particles diameters below of which lie 10%, 50%, and 90% of a sample's cumulative particle volume, respectively. **Figure 4d** shows that the percentiles of smGO and mGO in the oral phase are not significantly different than those for blank FFM; in **Figure 4e** it can be seen that the acidic conditions of the gastric




Figure 3. Colloidal stability of GO-enabled fasting food models. Time series over 10 min of mean diffusion coefficients (blue), polydispersity index (pdi, green), agglomeration index (ai, red), and kilo (photon) count per second (kcps, black) and their respective simple linear regressions in dashed lines for GO-enabled fasting food models. All metrics for a) smGO at 50 µg mL⁻¹, b) mGO at 50 µg mL⁻¹, and c) smGO at 250 µg mL⁻¹ remain unchanged over time. d) mGO at 250 µg mL⁻¹ only exhibited a slight increase in pdi over time (slope = 0.1).

phase inflate the $D_{,90}$ values of smGO and mGO at levels 3–4 higher than that for blank FFM. In the small intestinal phase described in Figure 4f, even though the pH of the digestive tract is neutral, smGO and mGO undergo further agglomeration that could be attributed to ion bridging between planar functional groups. The heatmap in Figure 4g summarizes the changes in size percentiles of smGO and mGO relative to blank FFM across the GIT.

In order to verify MALD measurements and observe micro-scale features of GO flakes, smGO, and mGO small intestinal digesta were imaged under FESEM, as presented in Figure 5, along with images of the as-prepared GO-enabled fasting food models. The applied protocol allowed us to visualize the flakes' morphology at the microscale and verify their agglomeration in small intestinal digesta by avoiding washing steps and other mechanical interventions that could bias the observed properties. In Figure 5a,b, flakes of the GO-enabled fasting food model appear flat and well-defined. In contrast, in Figure 5c,d, the small intestinal digesta of smGO and mGO appear agglomerated and thus larger in size, in agreement to

MALD measurements and similar to the effects of simple acid treatment on GO observed by others.^[24] Higher magnification images in Figure 5e,f reveal wrinkling and/or stacking of GO flakes which appear darker due to decreased conductivity and increased work function. Finally, the physisorption of carbonaceous material and ions might also contribute to the altered morphology of the flakes as they have been shown to enable the bridging of GO flakes and promote multiple stacking.^[48] Overall, FESEM images support the results from MALD regarding GO agglomeration and provide positive evidence for its morphological alterations during simulated digestion.

2.4. Chemical Transformations of GO across the Simulated Gastrointestinal Tract

Figure 6 presents XPS surface chemistry analyses on the small intestinal digesta of GO-enabled fasting food models and pristine GO samples. The C1s spectra of pristine GO in Figure 6a,b presents five main peaks around 284.8, 286.5, 288.1,




Figure 4. Volume-weighted size distributions and percentiles of cumulative particle volume for GO-enabled fasting food models and blank FFM. The evolution of volume-weighted particle diameters across a) oral, b) gastric, and c) small intestinal phases for GO-enabled fasting food models and blank FFM suggests extended agglomeration for smGO and mGO. d) In the oral phase, both samples share similar D_{10} , D_{50} , and D_{90} which are significantly elevated compared to blank FFM. e) In the gastric and f) small intestinal phase, D_{90} for smGO and mGO exhibit strong agglomeration. g) Heatmap for the visualization of \times -fold increase in D_{10} , D_{50} , and D_{90} of smGO and mGO over the respective values for blank FFM. Measurements were performed on GO-enabled fasting food models at $250 \mu\text{g mL}^{-1}$; statistical analyses were performed with Tukey's test for multiple comparisons; $**p < 0.01$; $***p < 0.001$; $****p < 0.0001$.

and 289.1 eV which correspond to sp^2 -hybridized C–C, C–O (epoxide and hydroxyl), C=O (carbonyl), and O–C=O (carboxyl) bonds, respectively. Small intestinal digesta of smGO and mGO, as shown in Figure 6c,d, respectively, present with overall increase in nitrogen content, along with a C–N peak at 285.8 eV in C1s spectra, indicating nitrogen incorporation into the GO structure. C–N peak increases for both smGO and mGO, accompanied by considerable increase in the C–C peak and restoration of sp^2 -hybridized C–C bonds. This observation indicates nitrogen substitution on smGO and mGO through multiple routes, including nucleophilic epoxide ring opening, amine participation in hydrogen bonds with hydroxyl groups, and/or deprotonation of carboxyl groups. These reactions primarily substitute the oxygen on the surface with nitrogen-containing functional groups, hence increasing the C–N peak. Later, upon further reactions with other reactants (simple protons or long-chained molecules), these nitrogen-containing groups leave the GO surface to facilitate C–C bond formation and reduce it by restoring its sp^2 -hybridized structure. Many GO reduction reaction pathways initiated by nitrogen-containing compounds have been reported in the literature.^[49] Biomolecules such as hormones, proteins, amino acids, serum albumin, and even microorganisms are among these nitrogen-containing compounds that have been reported as reducing agents for GO.^[50–53] Since proteins are present during the mouth, gastric, and small intestinal phase, it is plausible that they participate in reductive reactions on the GO surface.

These results highlight the propensity of GO to oxidize the intestinal proteome and chemically sequester enzymes. Consequently, further investigation of the GO reduction mechanism, biochemical identification of nitrogen-containing species on its

surface, and interrogation of its interactions with easily oxidizable nutrients (e.g., Vitamin C) are warranted through single compound reaction screening and proteomic analysis of its biomolecular corona.

2.5. In Vitro Toxicological Assessment of Small Intestinal GO Digestas against a Tri-Culture Model of the Human Intestinal Epithelium

In this study, we utilized an advanced, tri-culture, small intestinal epithelial model to assess the acute pathogenicity of two distinct sizes of GO small intestinal digesta. **Figure 7** presents the results from the toxicological assessment of smGO and mGO. It is important to note that due to physiological dilutions in the GIT fluids and cell culture medium, the starting concentrations of GO-enabled fasting food models at 50 and $250 \mu\text{g mL}^{-1}$ correspond to administered concentrations to cells of ≈ 1 and $\approx 5 \mu\text{g mL}^{-1}$, respectively. **Figure 7a** shows that the transepithelial electrical resistance (TEER) values of intestinal epithelia treated with small intestinal digesta of blank FFM, smGO, or mGO were similar. These results suggest good cell layer integrity and intracellular tight junctions (TJs), which ensure the uncompromised function of the intestinal barrier. Furthermore, extracellular release of the cytoplasmic enzyme lactate dehydrogenase (LDH) due to ruptured cell membranes and apoptosis is a typical measurand of acute cytotoxicity. As shown in **Figure 7b**, small intestinal digesta of smGO or mGO did not induce cytotoxicity under the experimental conditions of this study. Similarly, no differences were observed in overall cell viability or mitochondrial enzymatic activity as shown in




Figure 5. FESEM imaging of smGO and mGO. Electron microscopy images of GO-enabled fasting food models at $5 \mu\text{g mL}^{-1}$ for a) smGO and b) mGO exhibit typical features for GO flakes, like angular shapes and flat morphology. Low magnification images of small intestinal digesta of GO-enabled fasting food model at $250 \mu\text{g mL}^{-1}$ for c) smGO and d) mGO with their respective higher magnification images in (e,f) show agglomeration, multiple stacking, and physisorption of amorphous material.

Figure 7c upon exposure to small intestinal digesta of GO-enabled fasting food models. Figure 7d presents the assessment of reactive oxygen species (ROS) generation measured after 6 h of exposure to small intestinal digesta of smGO or mGO. Persistent ROS generation has been mechanistically linked to chronic inflammation and tissue injury and is one of the most studied mechanisms of ENMs toxicity.^[54,55] Here, at $1 \mu\text{g mL}^{-1}$ of administered GO concentration, there was no effect on ROS production. On the contrary, both smGO and mGO at $5 \mu\text{g mL}^{-1}$ of administered concentration caused a statistically significant 1.2-fold increase in ROS production over the blank

FFM, respectively ($p < 0.05$). Still, this increase is low compared to the positive control (menadione, $100 \times 10^{-6} \text{ M}$), which induced a 2.4-fold increase ($p < 0.001$) over the blank FFM.

The toxicity results here do not contradict the available literature on the biological effects of ingested GO. Guarnieri et. al. conducted the simulated digestion of GO flakes with lateral size $\approx 400 \text{ nm}$ at comparable concentrations and applied the digested GO on a Caco-2 cell monolayer without observing considerably different biological responses.^[26] Another study mimicked the stomach transition of GO by acid treatment (without digestive enzymes) and, again, no differences in cell viability were




Figure 6. Surface chemistry of GO-enabled fasting food models and GO small intestinal digesta. C1s XPS spectra of as-prepared a) smGO and b) mGO fasting food models. C1s XPS spectra of small intestinal digesta for c) smGO and d) mGO.

observed against Caco-2 cells at concentrations ranging from 5 to 80 $\mu\text{g mL}^{-1}$.^[24] However, variable ROS production was observed for GO of different sizes and starting materials. Finally, other studies skipped any semblance of simulated digestion and exposed Caco-2 cells to GO dispersed in culture medium alone, again without observing any acute toxicity.^[22,56]

The current toxicological evaluation of GO provides safety information for its application in water purification and remediation industries as well as useful insight for its use in the food industry, especially when put in context with commonly used ENMs, like TiO_2 and SiO_2 . The in vitro toxicity of TiO_2 and SiO_2 has been previously evaluated by the authors using the same GIT simulator and tri-culture intestinal epithelium model.^[57] At Food & Drug Administration (FDA) allowable concentrations ($\approx 210 \mu\text{g mL}^{-1}$ when administered to cells), SiO_2 did not induce any significant toxicological response, while TiO_2 only induced a significant ROS production (1.20-fold increase compared to untreated control, $p < 0.05$). Similar levels of biological activity between FDA-approved ENMs and GO suggest that at the tested experimental conditions GO may lack acute in vitro pathogenicity.

Representative TEM images presented in Figure 7e,f further show that GO did not induce any obvious histological alterations to the small intestinal epithelium. Specifically, the cellular tri-culture in vitro model employed here consisted of enterocytes, goblet cells, and M cells with clear polarization, TJs, and

dense apical brush border (BB) with microvilli (MV) at typical length and width of ≈ 1 and $\approx 0.1 \mu\text{m}$, respectively.^[58] Absence of BB disruption, maintained TJs, and no change in the MV number or length 24 h post-treatment of the epithelium with small intestinal digestas of GO-enabled fasting food models suggest that the barrier integrity was not compromised. Of note, no uptake of GO could be observed, which is in agreement with a recent report which demonstrated how the BB of differentiated Caco-2 cells prevents adhesion and uptake of GO flakes by epithelial cells.^[25]

While this tri-culture model provides a physiologically relevant, in vitro representation of the human small intestinal epithelium and is therefore suitable for basic, acute toxicological assessments, real world exposure to GO through ingestion might happen over longer time-points and could involve alterations at the molecular level which are difficult to pinpoint within the context of a single in vitro study. Furthermore, this study addresses the knowledge gap of the biological activity of GO ingested with water, but it is important to note that GO ingestion may also take place in the presence of more complex food models. It has already been shown that certain ENMs have the capacity to alter the bioavailability of nutrients^[59] while others may increase the bioavailability of noxious agents, like pesticides.^[57] In addition, food matrix effects have been shown to modulate the bioactivity of ENMs,^[32,35] and the gut microbiome and proteome of animals is known to be sensitive to the




Figure 7. In vitro toxicological assessment of a triculture human intestinal epithelium model exposed to small intestinal phase digesta of smGO and mGO. a) Trans-epithelial electrical resistance (TEER) measurements in $\Omega \text{ cm}^2$ (24 h), b) cytotoxicity assessment by lactate dehydrogenase (LDH) release assay as % of lysed control (24 h), c) cell viability/mitochondrial enzymatic activity (PrestoBlue assay) as % change compared to blank fasting food model (24 h), d) reactive oxygen species (ROS) generation as \times -fold change compared to blank fasting food model (6 h). e) Representative transmission electron microscopy (TEM) images of cryo-sectioned small intestinal epithelium after 24 h exposure with blank fasting food model or f) mGO at starting concentration of $250 \mu\text{g mL}^{-1}$. All experiments were performed in triplicates; error bars represent mean \pm standard deviation. $*p < 0.05$; $***p < 0.001$.

presence of chemically active particulates.^[28,29,60] Therefore, we plan to apply the methods developed here to interrogate the physicochemical transformations, toxicological assessment, and effect on gut microbiome and proteome of GO in the presence of more complex food models.

3. Conclusions

In this study, the size-sorted synthesis of endotoxin-free GO was presented. Additionally, its physicochemical transformations across the GIT and toxicological assessment against a physiologically relevant cellular in vitro model of the human intestinal epithelium were evaluated. During simulated gastrointestinal digestion, GO was shown to progressively agglomerate in the gastric and small intestinal phases. Importantly, both sub-micrometer- and micrometer-sized GO flakes exhibited a strong tendency to agglomerate. The observed morphological changes can be attributed to the acidic pH of the gastric phase which is known to promote GO agglomeration. Moreover, the abundance of proteins and cations across the GIT may also stabilize GO agglomerates or enable associations with different regions of the same flake, thus leading to folding and wrinkling. Our results further showed that GO is chemically reduced during simulated digestion and reacts with digestive enzymes, resulting in covalently bound N-containing groups on its surface. Toxicological assessment of the GO small intestinal digesta over 24 h did not show any acute cytotoxicity.

Importantly, both GO sizes elicited an $\approx 20\%$ statistically significant increase in ROS generation after 6 h which raises some concerns regarding its effects on tissues that are less tolerant to inflammagens, like in the case of inflammatory bowel diseases.

Under the light of this data, it is important to perform additional studies that take into consideration possible food matrix effects on the physicochemical transformations and biological profile of GO. Beyond its toxicological investigation, it is also important to examine the interactions of GO with the intestinal proteome and microbiota which may incur undesirable changes in the homeostasis of the intestinal tract, interfere with digestive processes, and modulate the bioavailability of macro and micronutrients.

4. Experimental Section

Synthesis and Size-Sorting of Pristine Graphene Oxide: Synthesis of endotoxin-free graphene oxide was performed by the oxidation of graphite under acidic conditions according to an improved Hummer's method developed by the authors and previously described elsewhere.^[37] After the purification step, endotoxin-free water was added to graphite oxide in a 200 mL beaker to obtain a 1 mg mL^{-1} solution. This sample was ultrasonicated using a probe sonicator (Q-sonica 700) at 20% amplitude for 30 min. Both dispersions were transferred to sterile centrifugation tubes and were centrifuged at 4000 rpm ($3220 \times g$) for 30 min to remove large flakes and graphitic aggregates. The supernatant of this dispersion was centrifuged at 20 000 rpm for 30 min. The precipitate was collected and re-dispersed in endotoxin-free water at the original dispersion volume. This sample was then centrifuged again at 5000 rpm for 30 min

and the resulting supernatant was collected and centrifuged again at 10 000 rpm for 30 min. The precipitate was re-dispersed in endotoxin-free water at 1 mg mL⁻¹ and used as mGO in further experiments. The supernatant was further centrifuged at 15 000 rpm for 30 min and the resulting precipitate was used as smGO for further experiments. Microbiological sterility and absence of endotoxins were experimentally verified as described in the Supporting Information.

Size Measurement of Graphene Oxide Using Field Emission Scanning Electron Microscopy: Silicon wafers (0.5 × 5 × 7 mm) were sputter coated with 10 nm of Pt/Pd in an EMS 150T S metal sputter coater and 5 μL drops of smGO or mGO at 0.5 μg mL⁻¹ were deposited on their surface and left to dry protected from dust. The wafers were then secured on aluminum stubs with thin strips of conductive tape and were imaged using a Supra 55VPTM (Carl Zeiss AG) at a working distance of 3–4 mm using the in-lens detector operating at 1 kV. For size measurements, flat GO flakes were identified, their surface was calculated using ImageJ, and distributions of the square root of as-measured surface area were plotted on GraphPad Prism.

Size Measurement of Graphene Oxide Using Atomic Force Microscopy (AFM): A drop of smGO or mGO suspensions at 0.01 mg mL⁻¹ was placed on an AFM-grade mica substrate. After 30 min, the sample was washed by deionized water for 5 s and dried using N₂ gas twice to assure the removal of aggregated particles and impurities. AFM images were obtained using a research asylum AFM in tapping mode using 9 nm thick silicon tip. Images were taken at various spots on the sample at 0.7 Hz scanning rate. Features with heights larger than 5 nm appeared to be GO aggregates and were not used in the image analysis. Obtained images were processed individually and manually using the Gwyddion software to evaluate the thickness of the flakes.

Raman Spectroscopy of Graphene Oxide: Dispersions of smGO and mGO at 0.5 mg mL⁻¹ concentration were used to prepare the Raman sample. 20 mL of each GO suspension was vacuum filtered over a polytetrafluoroethylene membrane (0.2 μm pore size). The samples were then dried in an oven at 80 °C for 10 h and were then mounted on a glass slide using double-sided tape to achieve a flat surface during the measurement. A Horiba Jobin-Yvon LabRam Raman microscope was used for the measurements with a laser source of 532 nm. The samples were scanned over a range of 1000–3000 cm⁻¹ Raman shift using 10 s acquisition times for five times on each point and 1800 g mm⁻¹ gratings were used during these measurements.

Dispersion Preparation of Graphene Oxide-Enabled Fasting Food Models: Under sterile conditions, 1 mL of each of the as-synthesized suspensions of pristine smGO and mGO were transferred in sterile, nonpyrogenic, 14 mL, polypropylene, round-bottom tubes. The tubes were then sonicated in a 3 in. cup-horn sonicator (Branson Ultrasonics Corp.) that delivered 1.23 J s⁻¹, as determined by a calorimetric calibration protocol described elsewhere.^[61] Each aliquot was sonicated for 60 s so that the total energy delivered to each suspension was ≈75 J. The sonicated, suspensions of pristine smGO and mGO were then added to appropriate volumes of endotoxin-free HyClone cell culture grade water at pH 7 and mixed by tube inversion at final GO concentration of 50 and 250 μg mL⁻¹, thus preparing graphene oxide-enabled fasting food models. HyClone cell culture grade water alone was used as a blank fasting food model (blank FFM).

Colloidal Characterization of Graphene Oxide-Enabled Fasting Food Models: Measurements of mean diffusion coefficient (*D*), pdi, and ai of the as-prepared smGO and mGO at 50 and 250 μg mL⁻¹ were performed using a Zetasizer NanoZS instrument by Malvern Instruments Ltd. Immediately after preparation, 1 mL aliquots of each sample were transferred in 12 mm disposable, polystyrene cuvettes. Each sample was illuminated with a 633 nm He–Ne laser beam and *D* and pdi values were calculated in regular time intervals according to the ISO recommended cumulants analysis of the correlograms. The agglomeration indices reported here are defined as the ratio of kilo (photon) counts per second (kcps) at 175° to kcps at 13°, normalized against its value at *t* = 0 min. For all samples, measurements were performed at 25 °C and measurement position and laser attenuation were set automatically by the instrument. Moreover, the scattering intensity for each sample in kcps was recorded

at 175° in regular time intervals. Time-resolved kcps values of smGO and mGO at 175° were recorded every second from freshly prepared samples using the “flow” measurement type. Finally, the obtained time series of *D*, pdi, ai, and kcps were fitted with GraphPad Prism using simple linear regression and it was tested if the slopes were significantly nonzero, thus indicating a temporal change in colloidal properties.

Digestion of Graphene-Oxide Enabled Fasting Food Models Using a Three-Phase Gastro-Intestinal Tract Simulator: 5 mL of smGO or mGO at 50 or 250 μg mL⁻¹ were used as initial food inputs to simulate the digestion of 1.250 or 0.250 mg of GO-enabled membranes, respectively. An equal volume of HyClone cell culture grade, endotoxin-free water at pH 7 was used as the blank fasting food model (blank FFM). In total, five samples were generated: 1) blank FFM; 2) smGO at 50 μg mL⁻¹; 3) smGO at 250 μg mL⁻¹; 4) mGO at 50 μg mL⁻¹; and 5) mGO at 250 μg mL⁻¹. The in vitro simulated digestion of the above samples was performed using a three-phase (oral, gastric, small intestinal) gastrointestinal tract simulator, as previously described in detail by the authors.^[36] Briefly, in the oral phase, food inputs were brought to 37 °C, mixed with simulated saliva fluid prewarmed at 37 °C, and inverted by hand for 10 s to mimic agitation in the mouth. The resulting oral phase digestas were then combined with prewarmed simulated gastric fluid and incubated in a shaking incubator at 37 °C for 2 h at 200 rpm to complete the stomach phase. In the small intestinal phase, stomach digestas were combined with prewarmed solutions containing additional salts, bile extract, and lipase to simulate intestinal fluid, and were incubated at 37 °C for 2 h.

Multi-Angle Laser Diffraction Measurements of Oral, Gastric, and Small Intestinal Digestas: A laser diffraction particle size analyzer (Mastersizer 3000, Malvern Instruments, Ltd.) equipped with a wet dispersion unit (Hydro SV) and 633 and 466 nm laser sources was used to measure the volume-weighted particle size distributions in the oral, gastric, and small intestinal digestas of smGO and mGO at 250 μg mL⁻¹. To perform background measurements, blank FFM samples corresponding to each of the oral, gastric, and small intestinal phase were diluted 1-in-7 with HyClone cell culture grade water and centrifuged at 10 000 × *g* for 10 min. The supernatants were then aspirated and used to correct for light refraction and background noise from the continuous phase. Oral, gastric, and small intestinal digestas of smGO, mGO, and blank FFM were diluted 1-in-7 with HyClone cell culture grade water and measured while stirred at 1800 rpm. For all samples, selected dispersant type was “water,” selected particle type was “nonspherical,” and the refractive index, absorption index, and density were set at 1.7, 0.01, and 2 g cm⁻³, respectively, for both 633 and 466 nm light measurements. For each sample, <10 measurements of 120 s (at 633 nm) and 10 s (at 466 nm) each were performed. Finally, the volume-weighted size distributions were averaged using the built-in software. For each of the oral, gastric, and small intestinal phase, multiple comparison tests between the *D*_{v10}, *D*_{v50}, and *D*_{v90} values of blank FFM and each of smGO and mGO were performed on GraphPad Prism using Tukey’s test.

Field-Emission Scanning Electron Microscopy of Graphene Oxide in Small Intestinal Digestas: Silicon wafers (0.5 × 5 × 7 mm) were sputter coated with 10 nm of Au in an EMS 150T S metal sputter coater and placed in 24-well plates. Each well was then filled with 2 mL of small intestinal phase digestas of smGO or mGO at 250 μg mL⁻¹ and placed at 4 °C protected from light for 3 days. 1 mL of pure glycerol was then added in each well to gently displace the sediments of digestas and reveal the wafers, which were transferred to new wells filled with deionized water. Importantly, only water and glycerol were used during sample preparation, the latter being a typical stabilizer of the tertiary structure of proteins.^[62] After standing overnight, the wafers were allowed to dry protected from dust. For field-emission scanning electron microscopy, the wafers were secured on aluminum stubs with thin strips of conductive tape and were imaged using a Supra 55VPTM (Carl Zeiss AG) at a working distance of 3–4 mm using the in-lens detector operating at 1 kV.

X-Ray Photoelectron Spectroscopy of Graphene Oxide in Small Intestinal Digestas: 10 mL of each of the smGO and mGO at 250 μg mL⁻¹ were vacuum filtered onto separate poly-ethersulfone (PES) membranes (Supor PES Membrane Disc Filters, Pall Corp.), thus fabricating

smGO-PES and mGO-PES membranes. Each of the as-prepared membranes was cut into half: one-half underwent simulated digestion as described above and the other half was left untreated (control). At the end of the small intestinal digestion phase, smGO-PES and mGO-PES were immersed in deionized water for 12 h and were then allowed to dry overnight protected from dust and light. For XPS analysis, digested membranes and their respective controls were analyzed by a Thermo Scientific K-Alpha XPS (ESCA). The X-rays were generated by a 12 keV electron beam and had a spot size of 400 nm. The atomic percentages of each atom and the C1s peak deconvolution were performed by using the Thermo Scientific Avantage software. Three data points for each sample were taken. The dwell time was set to 10 ms for the survey spectra and 50 ms for the high-resolution (C1s) spectra. For each data point, the number of scans was set to 3 and 4 for the survey and high-resolution scans, respectively. The XPS instrumental error for atomic composition is $\pm 1\%$, and the accuracy of the C1s peak fitting is $\pm 2\%$. Data represent the average of three independent measurements.

Tri-Culture, Small Intestinal Epithelium Cell Model and Treatments: Caco-2, HT29-MTX, and Raji-B cells were obtained from Sigma, Inc. Monocultures of Caco-2 and HT29-MTX cells were grown in high-glucose DMEM supplemented with 10%, v/v heat-inactivated fetal bovine serum (FBS). Raji B cells were cultured in RPMI 1640 media supplemented with 10% FBS.

A tri-culture, small intestinal epithelial model as previously described and characterized in detail by the authors was employed in this study.^[36] In summary, 1.5 mL of Caco-2 cells and HT29-MTX cells were first co-cultured at a ratio of 3:1 (Caco-2:HT29-MTX) for 2 weeks on a 0.4 μm pore membrane transwell inserts (apical compartment) in a 6-well cell culture plate. In the basolateral compartment, 2.5 mL of complete DMEM media was added. After day 4 and until day 15, media was changed every other day. During this time, Caco-2 cells differentiated to intestinal enterocytes and HT29-MTX cells secreted mucus, similar to intestinal goblet cells. On day 15 and 16, the media in the basolateral compartment was replaced with 2.5 mL of Raji B cell suspension at a concentration of 1×10^6 cells mL^{-1} in 1:1 DMEM:RPMI complete media to stimulate the differentiation of some of the mature Caco-2 cells to M-cell-like phenotype. Co-cultures of Caco-2/HT29-MTX in 96-well plates were used for tetrazolium salt reduction and ROS production studies (see below) which require closed-bottom adherent cell cultures suitable for plate reader fluorescence measurements. To prepare co-cultures, Caco-2 and HT29-MTX cells at a 3:1 ratio was seeded at a total 3×10^4 cells per well (100 μL of cell mixture) in black-wall, clear optical bottom plates (BD Biosciences). After day 4 and until day 18, media was changed every other day.

The small intestinal phase digestas were combined with FBS-free DMEM at a ratio of 1:3 and the mixtures were applied to the cells on day 17 (1.5 mL to the apical compartment for transwell inserts, 200 μL per well for 96-well plates). It is worth noting that the initial GO concentrations in smGO and mGO were diluted by a factor of 48 before being applied to cells. Therefore, the triculture cellular model was eventually exposed to 1.04 and 5.21 $\mu\text{g mL}^{-1}$ corresponding to starting smGO and mGO concentrations of 50 and 250 $\mu\text{g mL}^{-1}$, respectively.

Lactate Dehydrogenase Release, Intracellular Enzymatic Activity, Trans-Epithelial Resistance, and Intracellular Reactive Oxygen Species Generation: TEER was measured after 24 h treatment in transwell plate using an EVOM2 Epithelial Volt/Ohm Meter with a Chopstick Electrode Set (World Precision Instruments).

Cytotoxicity was performed after 24 h treatment in transwell tricultures using the Pierce LDH assay kit (Sigma Aldrich, St. Louis, MO, USA) according to manufacturer's instructions. Briefly, untreated wells were used to measure spontaneous LDH release and lysed wells were used to measure maximum LDH release. Apical fluid from each well was transferred to a tube and was then centrifuged. After centrifugation, 50 μL of each supernatant was dispensed in a fresh 96-well plate where 50 μL of reaction mixture was added. Plates were incubated at room temperature for 30 min after which 50 μL of stop solution was added and mixed by tapping. Absorbance was measured at 490 nm (A490) and 680 nm (A680). To calculate LDH activity, A680 values were subtracted

from A490 values to correct for instrument background. To correct for digesta background, LDH activities from no-cell controls were subtracted from test well LDH activities. Percent cytotoxicity was calculated by subtracting spontaneous LDH release values from treatment values, dividing by total LDH activity (Maximum LDH activity—Spontaneous LDH activity), and multiplying by 100.

ROS analysis was performed after 6 h treatment in 96-well plate co-cultures. Production of ROS was assessed using the CellROX green reagent (Thermo Fisher Scientific, Waltham, MA, USA) according to the manufacturer's instructions. Briefly, media was removed from the test wells, replaced with 100 μL of working solution, and plates were incubated for 30 min at 37 $^{\circ}\text{C}$. Wells were then washed three times with phosphate-buffered saline (PBS) and fluorescence was measured at 480 nm (excitation)/520 nm (emission). Cells treated with 100×10^{-6} M menadione for 1 h at 37 $^{\circ}\text{C}$ were used as positive controls for ROS generation.

PrestoBlue metabolic activity (cell viability) assay was performed after 24 h exposure using cells in 96-well plate co-cultures. PrestoBlue cell viability reagent (ThermoFisher) was used according to the manufacturer's instructions. Briefly, wells were washed three times with 200 μL of PBS, and 100 μL of 10% PrestoBlue reagent was added to each well. Plates were then incubated at 37 $^{\circ}\text{C}$ for 15 min and fluorescence was measured at 560 nm (excitation)/590 nm (emission).

Experiments were performed in triplicates and statistical analyses were performed on GraphPad Prism using two-way ANOVA tests and multiple comparisons (corrected with Dunnett's test).

Transmission Electron Microscopy: Transwell membranes were immersed in a routine fixative of 2.5% glutaraldehyde, 1.25% formaldehyde, and 0.03% picric acid in 0.1 M sodium cacodylate buffer (pH 7.4). After overnight fixation at room temperature, membranes were washed in 0.1 M cacodylate buffer and post-fixed with 1% osmium tetroxide (OsO_4)/1.5% potassium ferrocyanide (KFeCN_6) for 1 h, washed twice in water, once in maleate buffer (MB), and incubated in 1% uranyl acetate in MB for 1 h, followed by two washes in water and subsequent dehydration in grades of alcohol (10 min each; 50%, 70%, 90%, 2×10 min 100%). The samples were then put in propylene oxide for 1 h and infiltrated overnight in a 1:1 mixture of propylene oxide and TAAB Epon (Marivac Canada Inc. St. Laurent, Canada). The following day the samples were embedded in TAAB Epon and polymerized at 60 $^{\circ}\text{C}$ for 48 h. Ultrathin sections (≈ 60 nm) were cut on a Reichert Ultracut-S microtome, picked up on to copper grids stained with lead citrate and examined in a JEOL 1200EX transmission electron microscope and images were recorded with an AMT 2k CCD camera.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

D.B., D.P., X.C., C.A.A. contributed equally to this work. Research reported in this publication was supported by National Institute of Environmental Health Sciences Grants U24ES026946 and U01ES027292. The content is solely the responsibility of the authors and does not necessarily represent the official views of the National Institutes of Health. The engineered nanomaterial used in the research presented in this publication were synthesized, characterized, and provided by the Engineered Nanomaterials Resource and Coordination Core established at Harvard T. H. Chan School of Public Health (NIH grant #U24ES026946) as part of the Nanotechnology Health Implications Research (NHIR) Consortium. Support for the reported research, analysis of data, and result interpretation were also provided by the Nanyang Technological University – Harvard T. H. Chan School of Public Health Initiative for Sustainable Nanotechnology (NTU-Harvard

SusNano; NTU-HSPH 17001). Partial funding for Dimitrios Bitounis was provided by the International Initiative for the Environment and Public Health Cyprus Program of the Harvard School of Public Health.

Conflict of Interest

The authors declare no conflict of interest.

Keywords

agglomeration, graphene oxide, human intestinal epithelium, ingestion, toxicity

Received: December 29, 2019

Revised: February 20, 2020

Published online: March 20, 2020

- [1] W. J. Ong, L. L. Tan, Y. H. Ng, S. T. Yong, S. P. Chai, *Chem. Rev.* **2016**, *116*, 7159.
- [2] F. Bonaccorso, A. Bartolotta, J. N. Coleman, C. Backes, *Adv. Mater.* **2016**, *28*, 6136.
- [3] R. Kurapati, K. Kostarelos, M. Prato, A. Bianco, *Adv. Mater.* **2016**, *28*, 6052.
- [4] L. Wang, Q. Xiong, F. Xiao, H. Duan, *Biosens. Bioelectron.* **2017**, *89*, 136.
- [5] K. S. Novoselov, A. K. Geim, S. V. Morozov, D. Jiang, Y. Zhang, S. V. Dubonos, I. V. Grigorieva, A. A. Firsov, *Science* **2004**, *306*, 666.
- [6] K. Ghaffarzadeh, *J. Coord. Chem.* **2008**, *61*, 2990.
- [7] V. H. Pham, T. V. Cuong, S. H. Hur, E. W. Shin, J. S. Kim, J. S. Chung, E. J. Kim, *Carbon* **2010**, *48*, 1945.
- [8] C. A. Amadei, P. Arribas, C. D. Vecitis, *Carbon* **2018**, *133*, 398.
- [9] J. S. Cho, W. Jang, S. C. Mun, M. Yi, J. H. Park, D. H. Wang, *Carbon* **2018**, *139*, 564.
- [10] J. Pyun, *Angew. Chem., Int. Ed.* **2011**, *50*, 46.
- [11] L. Feng, L. Wu, X. Qu, *Adv. Mater.* **2013**, *25*, 168.
- [12] A. M. Pinto, J. Cabral, D. A. P. Tanaka, A. M. Mendes, F. D. Magalhães, *Polym. Int.* **2013**, *62*, 33.
- [13] J. Chen, L. Sun, Y. Cheng, Z. Lu, K. Shao, T. Li, C. Hu, H. Han, *ACS Appl. Mater. Interfaces* **2016**, *8*, 24057.
- [14] G. Reina, J. M. González-Domínguez, A. Criado, E. Vázquez, A. Bianco, M. Prato, *Chem. Soc. Rev.* **2017**, *46*, 4400.
- [15] H. M. Hegab, L. Zou, *J. Membr. Sci.* **2015**, *484*, 95.
- [16] H. Ali-Boucetta, D. Bitounis, R. Raveendran-Nair, A. Servant, J. Van den Bossche, K. Kostarelos, *Adv. Healthcare Mater.* **2013**, *2*, 433.
- [17] V. Palmieri, G. Perini, M. De Spirito, M. Papi, *Nanoscale Horiz.* **2019**, *4*, 273.
- [18] Y. H. Kim, M. S. Jo, J. K. Kim, J. H. Shin, J. E. Baek, H. S. Park, H. J. An, J. S. Lee, B. W. Kim, H. P. Kim, K. H. Ahn, K. S. Jeon, S. M. Oh, J. H. Lee, T. Workman, E. M. Faustman, I. J. Yu, *Nanotoxicology* **2018**, *12*, 224.
- [19] C. A. Amadei, A. Montessori, J. P. Kadow, S. Succi, C. D. Vecitis, *Environ. Sci. Technol.* **2017**, *51*, 4280.
- [20] S. Y. Wu, S. S. A. An, J. Hulme, *Int. J. Nanomed.* **2015**, *2015*, 9.
- [21] S. Y. Kwak, T. T. S. Lew, C. J. Sweeney, V. B. Koman, M. H. Wong, K. Bohmert-Tatarev, K. D. Snell, J. S. Seo, N. H. Chua, M. S. Strano, *Nat. Nanotechnol.* **2019**, *14*, 447.
- [22] T. H. D. Nguyen, M. Lin, A. Mustapha, *J. Food Prot.* **2015**, *78*, 996.
- [23] O. N. Ruiz, K. A. S. Fernando, B. Wang, N. A. Brown, P. G. Luo, N. D. McNamara, M. Vangsness, Y. P. Sun, C. E. Bunker, *ACS Nano* **2011**, *5*, 8100.
- [24] M. Kucki, P. Rupper, C. Sarrieu, M. Melucci, E. Treossi, A. Schwarz, V. León, A. Kraegeloh, E. Flahaut, E. Vázquez, V. Palermo, P. Wick, *Nanoscale* **2016**, *8*, 8749.
- [25] M. Kucki, L. Diener, N. Bohmer, C. Hirsch, H. F. Krug, V. Palermo, P. Wick, *J. Nanobiotechnol.* **2017**, *15*, 46.
- [26] D. Guarnieri, P. Sánchez-Moreno, A. E. Del Rio Castillo, F. Bonaccorso, F. Gatto, G. Bardi, C. Martín, E. Vázquez, T. Catelani, S. Sabella, P. P. Pompa, *Small* **2018**, *14*, 1800227.
- [27] K. Yang, H. Gong, X. Shi, J. Wan, Y. Zhang, Z. Liu, *Biomaterials* **2013**, *34*, 2787.
- [28] Y. Xie, B. Wu, X. X. Zhang, J. Yin, L. Mao, M. Hu, *Chemosphere* **2016**, *144*, 1306.
- [29] J. Li, S. Yang, J. Yu, R. Cui, R. Liu, R. Lei, Y. Chang, H. Geng, Y. Qin, W. Gu, S. Xia, K. Chen, J. Kong, G. Chen, C. Wu, G. Xing, *RSC Adv.* **2018**, *8*, 31366.
- [30] I. S. Sohal, K. S. O'Fallon, P. Gaines, P. Demokritou, D. Bello, *Part. Fibre Toxicol.* **2018**, *15*, 29.
- [31] G. M. Deloid, X. Cao, R. M. Molina, D. I. Silva, K. Bhattacharya, K. W. Ng, S. C. J. Loo, J. D. Brain, P. Demokritou, *Environ. Sci.: Nano* **2019**, *6*, 2105.
- [32] Z. Zhang, R. Zhang, H. Xiao, K. Bhattacharya, D. Bitounis, P. Demokritou, D. J. McClements, *NanoImpact* **2019**, *13*, 13.
- [33] I. S. Sohal, Y. K. Cho, K. S. O'Fallon, P. Gaines, P. Demokritou, D. Bello, *ACS Nano* **2018**, *12*, 8115.
- [34] X. Cao, Y. Han, F. Li, Z. Li, D. J. McClements, L. He, E. A. Decker, B. Xing, H. Xiao, *NanoImpact* **2019**, *13*, 37.
- [35] D. J. McClements, G. DeLoid, G. Pyrgiotakis, J. A. Shatkin, H. Xiao, P. Demokritou, *NanoImpact* **2016**, *3–4*, 47.
- [36] G. M. DeLoid, Y. Wang, K. Kapronezai, L. R. Lorente, R. Zhang, G. Pyrgiotakis, N. V. Konduru, M. Ericsson, J. C. White, R. De La Torre-Roche, H. Xiao, D. J. McClements, P. Demokritou, *Part. Fibre Toxicol.* **2017**, *14*, 40.
- [37] D. Parviz, M. Strano, *Curr. Protoc. Chem. Biol.* **2018**, *10*, e51.
- [38] J. Jia, C. M. Kan, X. Lin, X. Shen, J. K. Kim, *Carbon* **2014**, *77*, 244.
- [39] J. I. Joon, *New Developments in Photon and Materials Research*, Nova Science Publishers, Inc, New York **2013**.
- [40] A. Montessori, C. A. Amadei, G. Falcucci, M. Sega, C. D. Vecitis, S. Succi, *Europhys. Lett.* **2016**, *116*, 54002.
- [41] C. A. Amadei, C. D. Vecitis, *J. Phys. Chem. Lett.* **2016**, *7*, 3791.
- [42] A. M. Dimiev, S. Eigler, *Graphene Oxide: Fundamentals and Applications*, John Wiley & Sons, Chichester, U.K. **2016**.
- [43] B. Konkena, S. Vasudevan, *J. Phys. Chem. Lett.* **2012**, *3*, 867.
- [44] V. V. Neklyudov, N. R. Khafizov, I. A. Sedov, A. M. Dimiev, *Phys. Chem. Chem. Phys.* **2017**, *19*, 17000.
- [45] M. M. Gudarzi, *Langmuir* **2016**, *32*, 5058.
- [46] J. Zhao, Z. Wang, J. C. White, B. Xing, *Environ. Sci. Technol.* **2014**, *48*, 9995.
- [47] L. Wu, L. Liu, B. Gao, R. Muñoz-Carpena, M. Zhang, H. Chen, Z. Zhou, H. Wang, *Langmuir* **2013**, *29*, 15174.
- [48] Y. Zhou, D. S. Fox, P. Maguire, R. O'Connell, R. Masters, C. Rodenburg, H. Wu, M. Dapor, Y. Chen, H. Zhang, *Sci. Rep.* **2016**, *6*, 21045.
- [49] C. K. Chua, M. Pumera, *Chem. Soc. Rev.* **2014**, *43*, 291.
- [50] S. Bose, T. Kuila, A. K. Mishra, N. H. Kim, J. H. Lee, *J. Mater. Chem.* **2012**, *22*, 9696.
- [51] D. Chen, L. Li, L. Guo, *Nanotechnology* **2011**, *22*, 325601.
- [52] J. Liu, S. Fu, B. Yuan, Y. Li, Z. Deng, *J. Am. Chem. Soc.* **2010**, *132*, 7279.
- [53] A. Esfandiari, O. Akhavan, A. Irajizad, *J. Mater. Chem.* **2011**, *21*, 10907.
- [54] L. Rubio, G. Pyrgiotakis, J. Beltran-Huarac, Y. Zhang, J. Gaurav, G. Deloid, A. Spyrogianni, K. A. Sarosiek, D. Bello, P. Demokritou, *Part. Fibre Toxicol.* **2019**, *16*, 40.
- [55] M. Khatri, D. Bello, J. Martin, A. Bello, R. Gore, P. Demokritou, P. Gaines, *NanoImpact* **2017**, *5*, 133.

- [56] N. Rahmanian, H. Hamishehkar, J. E. N. Dolatabadi, N. Arsalani, *Colloids Surf., B* **2014**, *123*, 331.
- [57] X. Cao, G. M. Deloid, D. Bitounis, R. De La Torre-Roche, J. C. White, Z. Zhang, C. G. Ho, K. W. Ng, B. D. Eitzer, P. Demokritou, *Environ. Sci.: Nano* **2019**, *6*, 2786.
- [58] S. W. Crawley, M. S. Mooseker, M. J. Tyska, *J. Cell Biol.* **2014**, *207*, 441.
- [59] G. M. Deloid, I. S. Sohal, L. R. Lorente, R. M. Molina, G. Pyrgiotakis, A. Stevanovic, R. Zhang, D. J. McClements, N. K. Geitner, D. W. Bousfield, K. W. Ng, S. C. J. Loo, D. C. Bell, J. Brain, P. Demokritou, *ACS Nano* **2018**, *12*, 6469.
- [60] Y. Zhao, X. Yu, R. Jia, R. Yang, Q. Rui, D. Wang, *Sci. Rep.* **2015**, *5*, 17233.
- [61] J. M. Cohen, J. Beltran-Huarac, G. Pyrgiotakis, P. Demokritou, *NanoImpact* **2018**, *10*, 81.
- [62] V. Vagenende, M. G. S. Yap, B. L. Trout, *Biochemistry* **2009**, *48*, 11084.